Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Http://www.aoc-cert.com Email: postmaster@aoc-cert.com

File administrators

Report No.:AOC250527010R

# **TEST REPORT**

|                          |                 | Sunny Su   | Alice Zhou               |
|--------------------------|-----------------|--|--------------------------|
| Written By:              | (               | Dunny Su Approved by:  | Alice zhou               |
| Signed for and on behalf | of AC           | CE   |                          |
| A RoHS Directive (EU     | J) 201<br>***** | 7/2102 amending Annex II to Directive 2011/65/EU.  | <b>POSITIVE</b>          |
| TEST REQUEST             |                 |  | CONCLUSION               |
| Summary of Test Result   | ts:             |  |                          |
| Results                  | ****            | Please refer to next page(s).  |                          |
| Testing Period           | :               | May 20, 2025 ~ May 27, 2025  |                          |
| Sample Receiving Date    | :               | May 20, 2025   |                          |
| Style/ Item No.          | :               | 9711AFDC   |                          |
| Trade Mark               | :               | Honor  |                          |
| Sample Name              | :               | Promotion materials, Universal Materials, Indoor | terial, SI 4.1, Luminous |
| Report on the submitted  | l san           | ples said to be:   |                          |
| Address                  | :               | Shang Keng Industrial District, Chang Ping Town Province, PRC  | Dongguan Guangdong       |
| Manufacturer             | :               | Dongguan Excel Jointure Acrylic Products LTD   |                          |
| Client address           | :               | Shang Keng Industrial District, Chang Ping Town Province, PRC  | Dongguan Guangdong       |
| Client company           | :               | Dongguan Excel Jointure Acrylic Products LTD   |                          |
|                          |                 |  |                          |

Manager

Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Http://www.aoc-cert.com Email: postmaster@aoc-cert.com

Report No.:AOC250527010R

## Results:

## A. EU RoHS Directive 2011/65/EU and its amendment directives on XRF

Test method: With reference to IEC 62321-3-1:2013, Screening by X-ray Fluorescence Spectroscopy (XRF)

| Seq. | Tootod Double)           | Results |    |    |    |    |  |  |  |
|------|--------------------------|---------|----|----|----|----|--|--|--|
| No.  | Tested Part(s)           | Pb      | Cd | Hg | Cr | Br |  |  |  |
| 1    | White plasitc enclosure  | BL      | BL | BL | BL | BL |  |  |  |
| 2    | Silver plasitc enclosure | BL      | BL | BL | BL | BL |  |  |  |
| 3    | Silver metal screw       | BL      | BL | BL | BL | BL |  |  |  |
| 4    | Acrylic sheet            | BL      | BL | BL | BL | BL |  |  |  |
| 5    | Lamp bead                | BL      | BL | BL | BL | BL |  |  |  |
| 6    | White wire               | BL      | BL | BL | BL | BL |  |  |  |
| 7    | USB interface            | BL      | BL | BL | BL | BL |  |  |  |
| 8    | Chips of resistance      | BL      | BL | BL | BL | BL |  |  |  |
| 9    | Chips of capacitance     | BL      | BL | BL | BL | BL |  |  |  |
| 10   | PCB                      | BL      | BL | BL | BL | BL |  |  |  |
| 11   | Solder on PCB            | BL      | BL | BL | BL | BL |  |  |  |

\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*

Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Http://www.aoc-cert.com Email: postmaster@aoc-cert.com

Report No.:AOC250527010R

#### Note:

-- = Not Conducted

\* = Screening by XRF and detected by chemical method. The test results of chemical method please refer to next pages.

i Results were obtained by XRF for primary screening, and further chemical testing by ICP (for Cd, Pb, Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs) are recommended to be performed, if the concentration exceeds the below warning value according to IEC 62321-3-1:2013.

| Element | Unit  | Non-metal   | Metal  | Composite Material                    |
|---------|-------|---|--|---------------------------------------|
| Cd      | mg/kg | BL≤70-3σ <x<br>&lt;130+3σ≤OL</x<br>   | BL≤70-3σ <x<br>&lt;130+3σ≤OL</x<br>                        | BL≤50-3σ <x<br>&lt;150+3σ≤OL</x<br>   |
| Pb      | mg/kg | BL≤700-3σ <x<br>&lt;1300+3σ≤OL</x<br>   | BL≤700-3σ <x<br>&lt;1300+3σ≤OL</x<br>                      | BL≤500-3σ <x<br>&lt;1500+3σ≤OL</x<br> |
| Hg      | mg/kg | BL≤700-3σ <x<br>&lt;1300+3σ≤OL</x<br>   | BL≤700-3σ <x<br>&lt;1300+3σ≤OL</x<br>                      | BL≤500-3σ <x<br>&lt;1500+3σ≤OL</x<br> |
| Cr      | mg/kg | BL≤700-3σ <x< td=""><td>BL≤700-3σ<x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<></td></x<> | BL≤700-3σ <x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<> | BL≤500-3σ <x< td=""></x<>             |
| Br      | mg/kg | BL≤300-3σ <x< td=""><td></td><td>BL≤250-3σ<x< td=""></x<></td></x<>                         |  | BL≤250-3σ <x< td=""></x<>             |

\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*

Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Http://www.aoc-cert.com Email: postmaster@aoc-cert.com

Report No.:AOC250527010R

#### Note:

BL = Below Limit
OL = Over Limit
X = Inconclusive

The XRF screening test for RoHS elements – The reading may be different to the actual content in the sample be of non-uniformity composition.

iii The maximum permissible limit is quoted from the document 2005/618/EC amending RoHS directive 2011/65/EU:

| RoHS Restricted Substances            | Maximum Concentration Value (mg/kg) (by weight in homogenous materials) |
|---------------------------------------|---|
| Cadmium (Cd)                          | 100   |
| Lead (Pb)                             | 1000  |
| Mercury (Hg)                          | 1000  |
| Hexavalent Chromium (Cr(VI))          | 1000  |
| Polybrominated biphenyls (PBBs)       | 1000  |
| Polybrominated diphenylethers (PBDEs) | 1000  |
| Bis(2-ethylhexyl) phthalate(DEHP)     | 1000  |
| Butyl benzyl phthalate(BBP)           | 1000  |
| Dibutyl phthalate(DBP)                | 1000  |
| Diisobutyl phthalate(DIBP)            | 1000  |

#### Disclaimers:

This XRF Screening report is for reference purposes only. The applicant shall make its/his/her own judgment as to whether the information provided in this XRF screening report is sufficient for its/his/her purposes.

The result shown in this XRF screening report will differ based on various factors, including but not limited to, the sample size, thickness, area, surface flatness, equipment parameters and matrix effect (e.g. plastic, rubber, metal, glass, ceramic etc.). Further wet chemical pre-treatment with relevant chemical equipment analysis are required to obtain quantitative data.

\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*

Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Http://www.aoc-cert.com Email: postmaster@aoc-cert.com

Report No.:AOC250527010R

## B. The Test Results of Chemical Method:

#### Test method:

Lead & Cadmium Content:

With reference to IEC 62321-5:2013, by acid digestion and analysis was performed by inductively coupled plasma atomic emission spectrometer (ICP-AES)

## Mercury Content:

With reference to IEC 62321-4:2013, by acid digestion and analysis was performed by inductively coupled plasma atomic emission spectrometer (ICP-AES)

#### **Hexavalent Chromium Content:**

With reference to IEC 62321-7-1:2013, by alkaline digestion and analysis was performed by UV-visible spectrophotometer (UV-Vis)

## PBBs & PBDEs Content:

With reference to IEC 62321-6:2015, by solvent extraction and analysis was performed by gas chromatographic-mass spectrometer (GC-MS)

#### Phthalates Content:

With reference to IEC 62321-8:2017, by gas chromatography-mass spectrometry (GC-MS)

## 1) The test results of Lead (Pb)

| Itam              | l lni4 | MDI | Res  | ults | Limit      |  |
|-------------------|--------|-----|------|------|------------|--|
| Item              | Unit   | MDL | (1)  | (2)  | Limit      |  |
| Lead Content (Pb) | mg/kg  | 2   | 38   | 21   | 1000 mg/kg |  |
| Conclusion        | 1      | 1   | Pass | Pass | /          |  |

\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*

Shenzhen AOCE Electronic Technology Service Co., Ltd. Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Email: postmaster@aoc-cert.com Http://www.aoc-cert.com

Report No.:AOC250527010R

## 2) The test results of PBBs & PBDEs

| lta-m   | I I I I I I I | MDI | Res  | ults | I imale    |
|---|---------------|-----|------|------|------------|
| Item  | Unit          | MDL | 1    | 2    | Limit      |
| Polybrominated Biphenyls (PBBs)                 |               |     |      |      |            |
| Monobromobiphenyl                               | mg/kg         | 5   | N.D. | N.D. |            |
| Dibromobiphenyl                                 | mg/kg         | 5   | N.D. | N.D. |            |
| Tribromobiphenyl                                | mg/kg         | 5   | N.D. | N.D. |            |
| Tetrabromobiphenyl                              | mg/kg         | 5   | N.D. | N.D. |            |
| Pentabromobiphenyl                              | mg/kg         | 5   | N.D. | N.D. |            |
| Hexabromobiphenyl                               | mg/kg         | 5   | N.D. | N.D. |            |
| Heptabromobiphenyl                              | mg/kg         | 5   | N.D. | N.D. |            |
| Octabromobiphenyl                               | mg/kg         | 5   | N.D. | N.D. |            |
| Nonabromodiphenyl                               | mg/kg         | 5   | N.D. | N.D. |            |
| Decabromodiphenyl                               | mg/kg         | 5   | N.D. | N.D. |            |
| Total content                                   | mg/kg         | 1   | N.D. | N.D. | 1000 mg/kg |
| Polybrominated Diphenylethers (PBDEs)(Mon-Deca) |               |     |      |      |            |
| Monobromodiphenyl ether                         | mg/kg         | 5   | N.D. | N.D. |            |
| Dibromodiphenyl ether                           | mg/kg         | 5   | N.D. | N.D. |            |
| Tribromodiphenyl ether                          | mg/kg         | 5   | N.D. | N.D. |            |
| Tetrabromodiphenyl ether                        | mg/kg         | 5   | N.D. | N.D. |            |
| Pentabromodiphenyl ether                        | mg/kg         | 5   | N.D. | N.D. |            |
| Hexabromodiphenyl ether                         | mg/kg         | 5   | N.D. | N.D. |            |
| Heptabromodiphenyl ether                        | mg/kg         | 5   | N.D. | N.D. |            |
| Octabromodiphenyl ether                         | mg/kg         | 5   | N.D. | N.D. |            |
| Nonabromodiphenyl ether                         | mg/kg         | 5   | N.D. | N.D. |            |
| Decabromodiphenyl ether                         | mg/kg         | 5   | N.D. | N.D. |            |
| Total content                                   | mg/kg         | 1   | N.D. | N.D. | 1000 mg/kg |

Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Http://www.aoc-cert.com Email: postmaster@aoc-cert.com

Report No.:AOC250527010R

| Itam                       | Unit    | Unit MDL |       |       | Results |       |       | Limit      |  |
|----------------------------|---------|----------|-------|-------|---------|-------|-------|------------|--|
| Item                       | Unit    | MDL      | (1)   | (2)   | (3)     | (4)   | (5)   | Limit      |  |
| Dibuyl Phthalate(DBP)      | mg/kg   | 50       | N.D.  | N.D.  | N.D.    | N.D.  | N.D.  | 1000 mg/kg |  |
| Benzylbutyl Phthalate(BBP) | mg/kg   | 50       | N.D.  | N.D.  | N.D.    | N.D.  | N.D.  | 1000 mg/kg |  |
| Bis(2-ethylhexyl)          | mg/kg   | 50       | N.D.  | N.D.  | N.D.    | N.D.  | N.D.  | 1000 mg/kg |  |
| Phthalate(DEHP)            | ilig/kg | 30       | IN.D. | IN.D. | IN.D.   | IN.D. | IN.D. | 1000 mg/kg |  |
| Diispbutyl phthalate(DIBP) | mg/kg   | 50       | N.D.  | N.D.  | N.D.    | N.D.  | N.D.  | 1000 mg/kg |  |

| Item                              | Unit  | MDL |      |      | Results |      |      | Limit      |  |
|-----------------------------------|-------|-----|------|------|---------|------|------|------------|--|
| item                              | Unit  |     | (6)  | (7)  | (8)     | (9)  | (10) | Lillit     |  |
| Dibuyl Phthalate(DBP)             | mg/kg | 50  | N.D. | N.D. | N.D.    | N.D. | N.D. | 1000 mg/kg |  |
| Benzylbutyl Phthalate(BBP)        | mg/kg | 50  | N.D. | N.D. | N.D.    | N.D. | N.D. | 1000 mg/kg |  |
| Bis(2-ethylhexyl) Phthalate(DEHP) | mg/kg | 50  | N.D. | N.D. | N.D.    | N.D. | N.D. | 1000 mg/kg |  |
| Diispbutyl phthalate(DIBP)        | mg/kg | 50  | N.D. | N.D. | N.D.    | N.D. | N.D. | 1000 mg/kg |  |

| Item                       | Unit  | MDL |       | Results |      | Limit      |  |
|----------------------------|-------|-----|-------|---------|------|------------|--|
| item                       | Unit  |     | (11)  | <br>    | <br> | Limit      |  |
| Dibuyl Phthalate(DBP)      | mg/kg | 50  | N.D.  | <br>    | <br> | 1000 mg/kg |  |
| Benzylbutyl Phthalate(BBP) | mg/kg | 50  | N.D.  | <br>    | <br> | 1000 mg/kg |  |
| Bis(2-ethylhexyl)          | ma/ka | 50  | N.D.  | <br>    | <br> | 1000 mg/kg |  |
| Phthalate(DEHP)            | mg/kg | 50  | IN.D. |         |      | 1000 mg/kg |  |
| Diispbutyl phthalate(DIBP) | mg/kg | 50  | N.D.  | <br>    | <br> | 1000 mg/kg |  |

\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*

## Note:

- N.D. = Not Detected or less than MDL

- mg/kg = ppm

- MDL = Method Detection Limit

- Photo appendix is included.

\*

Shenzhen AOCE Electronic Technology Service Co., Ltd. Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Email: postmaster@aoc-cert.com Http://www.aoc-cert.com

Report No.:AOC250527010R

## **Appendix**

## **Photograph of Sample**



Fig.1



Fig.2

Shenzhen AOCE Electronic Technology Service Co., Ltd. Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Email: postmaster@aoc-cert.com Http://www.aoc-cert.com

Report No.:AOC250527010R




Fig.3




Fig.4

AOCE authenticate the photo on original report only

\*\*\*\*\*\*\* End of Report \*\*\*\*\*\*\*\*\*